

## AMENDMENTS TO THE CLAIMS

1. (Currently Amended) A compound of molecular formula I,



wherein  $2.2 \leq x \leq 4$ ,  $0 < y < 2$  and  $z \geq 0$ .

2. (Currently Amended) A compound according to Claim 1, wherein formula I,

$2.2 \leq x \leq 4$  and  $0.1 \leq y \leq 1.75$ ,  $z = 0.5$  to  $2.6$ .

3. (Currently Amended) A compound according to Claim 1, wherein formula I,

$2.2 \leq x \leq 3.6$  and  $0.1 \leq y \leq 1.75$ .

4. (Original) A compound according to Claim 1, further characterised by the normalised crystallographic unit cell volume, when indexed in hexagonal symmetry to a R-3m structure, being smaller than that of  $\text{LiCrO}_2$  ie. smaller than 104.9 cubic Angstroms.

5. (Original) A compound according to Claim 1, further characterised by the average cation to anion bond distance being smaller than that of  $\text{LiCrO}_2$ .

6. (Original) A compound according to Claim 1, wherein formula I,  $x = 2.8$  to  $3.4$ ,  $y = 0.49$  to  $1.46$  and  $z = 0.5$  to  $2.6$ .

7. (Original) A compound according to Claim 1, wherein formula I,  $x = 2.8$  to  $3.4$ ,  $y = 1.01$  to  $1.46$  and  $z = 0.9$  to  $1.9$ .

8. (Original) A compound according to Claim 1, wherein formula I,  $x = 2.8$  to  $3.3$ ,  $y = 0.49$  to  $0.93$  and  $z = 0.5$  to  $2.6$ .
9. (Cancel) A compound according to Claim 1, wherein formula I,  $x = 2.04$  to  $3.44$ ,  $y = 0.51$  to  $1.34$  and  $z = 0.07$  to  $1.86$ .
10. (Original) A compound according to Claim 1, wherein formula I,  $x = 2.25$  to  $3.44$ ,  $y = 0.98$  to  $1.34$  and  $z = 0.37$  to  $1.86$ .
11. (Original) A compound according to Claim 1, wherein formula I,  $x = 3.15$  to  $3.30$ ,  $y = 0.89$  to  $1.09$  and  $z = 1.00$  to  $1.54$ .
12. (Original) A compound according to Claim 1, wherein formula I,  $x = 2.95$ ,  $y = 1.09$  and  $z = 0.11$ , further characterised by a normalised unit cell volume of  $102.1$  cubic angstroms and being indexed to a hexagonal crystallographic unit cell having dimensions  $a = 2.87\bar{6}$  angstroms,  $b = 2.87\bar{6}$  angstroms, and  $c = 14.25$  angstroms.
13. (Original) A cathode for use in a secondary lithium ion electrochemical cell, comprising as active material a compound of formula I as defined in Claim 1.
14. (Original) A secondary lithium ion electrochemical cell comprising, a lithium intercalation anode, a suitable non-aqueous electrolyte including a lithium salt, a cathode as defined in Claim 13, and a separator between the anode and cathode.
15. (Original) An electrochemical cell according to Claim 14, wherein the anode comprises a material selected from the group consisting of transition metal oxides, transition metal sulphides

and carbonaceous materials, and wherein the electrolyte is in liquid form and includes a suitable organic solvent.

16. (Original) An electrochemical cell according to Claim 15, wherein the lithium salt is selected from the group consisting of  $\text{LiAsF}_6$ ,  $\text{LiPF}_6$ ,  $\text{LiBF}_4$ ,  $\text{LiClO}_4$ ,  $\text{LiBr}$ ,  $\text{LiAlCl}_4$ ,  $\text{LiCF}_3\text{SO}_3$ ,  $\text{LiC}(\text{CF}_3\text{SO}_2)_3$ ,  $\text{LiN}(\text{CF}_3\text{SO}_2)_2$ , and mixtures thereof.
17. (Original) An electrochemical cell according to Claim 16, wherein the organic solvent is selected from the group consisting of propylene carbonate, ethylene carbonate, 2-methyl tetrahydrofuran, tetrahydrofuran, dimethoxyethane, diethoxyethane, dimethyl carbonate, diethyl carbonate, methyl acetate, methylformate,  $\gamma$ -butyrolactone, 1,3-dioxolane, sulfolane, acetonitrile, butyronitrile, trimethylphosphate, dimethylformamide and other like organic solvents and mixtures thereof.
18. (Original) An electrochemical cell according to Claim 17, wherein the anode comprises a carbonaceous material.
19. (Original) An electrochemical cell according to Claim 18, wherein the anode comprises a graphitic carbon.
20. (Original) An electrochemical cell according to Claim 18, wherein the electrolyte is a solid or gelled polymer.
21. (Original) An electrochemical cell according to Claim 18, wherein the electrolyte comprises 1 M  $\text{LiPF}_6$  in a 1:1 mixture of ethylene carbonate and dimethyl carbonate.

22. (Currently Amended) An electrochemical cell according to Claim 19, wherein formula I,  $x = \text{2.2 to 4}$  2.25-3.6,  $y = 0.1$  to 1.75 and  $z \geq 0$ .




## UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES DEPARTMENT OF COMMERCE  
 United States Patent and Trademark Office  
 Address: COMMISSIONER FOR PATENTS  
 P.O. Box 1450  
 Alexandria, Virginia 22313-1450  
 www.uspto.gov

APPLICATION NO.	FILING DATE	FIRST NAMED INVENTOR	ATTORNEY DOCKET NO.	CONFIRMATION NO.
09/857,701	08/20/2001	Yeong-Chang Yoo	11023-1	1047
7590	12/12/2003			
National Research Council of Canada Intellectual Property Services Office EG 12 Bldg M 58 Montreal Road Ottawa, K1A 0R6 CANADA			EXAMINER BELL, BRUCE F	
			ART UNIT 1746	PAPER NUMBER
DATE MAILED: 12/12/2003				

Please find below and/or attached an Office communication concerning this application or proceeding.



conveys desk